



讯科标准
XUNKE STANDARD

Test Report

Sample Name: KN95 protective mask

Client Name: Shenzhen Venfish Intelligent Technology Co., Ltd

Test sort: Commissioned test

Report date: 2020.03.06

(stamp of laboratory)



Shenzhen Xunke Standard Technology Service Co.,Ltd.

(Add.): 2nd Floor, Building E2, Qiangrong East Industrial Zone, Jiuwei Community,
Hangcheng Street, Baoan District, Shenzhen City, Guangdong Province, China.
Tel: (+86)-755-23727890 Fax: (+86)-755-23727890
Web: www.xktest.cn E-mail: cs@xktest.cn P.C.: 518126



讯科标准
XUNKE STANDARD

Test Report

No. XKS2020R03020207E

page 1 of 7

Detection Category	<input checked="" type="checkbox"/> Commissioned test <input type="checkbox"/> Routine test <input type="checkbox"/> Evaluation test <input type="checkbox"/> Type test		
Sample Source	<input checked="" type="checkbox"/> Client to send samples <input type="checkbox"/> Sampling		
Client	Shenzhen Venfish Intelligent Technology Co., Ltd		
Client Address	5 / F, building F, No. 4, yard 6, Dongcai Industrial Zone, Gushu community, Xixiang street, Bao'an District, Shenzhen		
Manufacturer	/		
Manufacturer Address	/		
Sample Name	KN95 protective mask	Logo	/
Sample Model	KN95	Production serial number	/
Sample quantity	40pcs	Sample number	XKS2020R03020207
Date of Sample Receive	2020.03.02	Test date	2020.03.02~2020.03.06
environment condition	temperature: 24.5℃ Relative humidity: 60%		
Test Method	EN 149:2001+A1:2009		
Requested/item	Performance Test		
Test Results	See the next page		
Note	1. Sample information provided by the client, only responsible for the incominsample. 2. The test results are for reference only.		

Written by: Jemy Li

Reviewed by: Huigang Cai

Approved By: Shunmei Cao





Test Report

No. XKS2020R03020207E

page 2 of 7

1. Test Method

According to EN 149:2001+A1:2009, perform performance tests on the samples submitted.

2. Test Results

Title	Requirement clause	Technical requirement	Test Result	Test conclusion
Visual inspection	7.3	Products need to have identification and manufacturing information	Meet the requirements	Qualified
Material	7.4	Particle filtering half masks shall be offered for sale packaged	Meet the requirements	Qualified
	7.5	1) Expose the particle filtering half masks to the following thermal cycle: a) for 24 h to a dry atmosphere of $(70 \pm 3)^{\circ}\text{C}$; b) for 24 h to a temperature of $(-30 \pm 3)^{\circ}\text{C}$; 2) Mechanical strength	Meet the requirements	Qualified
Clearing and disinfection	7.6	re-usable particle filtering half mask shall satisfy the penetration requirement of the relevant class	Meet the requirements	Qualified
Total inward leakage	7.9.1	based on til of each action $< 11\%$; based on overall til of human $< 8\%$	50 working TIL $< 11\%$ 9 subjects TIL $< 8\%$	Qualified
Compatibility with skin	7.10	Testing shall be done in accordance with 8.4 and 8.5.	Healthy without stimulation	Qualified
Flammability	7.11	Each part exposed to the flame shall not burn after being removed from the flame; if burning, the continuous burning time shall not exceed 5s.	Untreated sample 1	4s Qualified
			Untreated sample 2	3s Qualified
			Pretreatment sample 1	4s Qualified
			Pretreatment sample 1	3s Qualified

Test Report

No. XKS2020R03020207E

page 3 of 7

2. Test Results (Continued)

Title	Requirement clause	Technical requirement	Test Result	Test conclusion
Carbon dioxide content	7.12	$\leq 1\%$	0.6%	Qualified
Head harness	7.13	The head harness shall be adjustable or self-adjusting and shall be sufficiently robust to hold the particle filtering half mask firmly in position and be capable of maintaining total inward leakage requirements for the device.	Meet the requirements	Qualified
Field of vision	7.14	The field of vision is acceptable $\geq 60^\circ$	69°	Qualified
Exhalation valve	7.15	withstand axially a tensile force of 10N applied for 10s	Meet the requirements	Qualified
Breathing resistance	7.16	FFP1: ≤ 4 mbar	FFP2	Qualified
		FFP2: ≤ 5 mbar		
		FFP3: ≤ 7 mbar		
Clogging test (optional for FFP1+FFP2+FFP3 single shift use devices only)	7.17	FFP1 $\geq 80\%$ FFP2 $\geq 94\%$ FFP3 $\geq 97\%$	96.1%	Qualified
Demountable parts	7.18	readily connected and secured	Meet the requirements	Qualified
Note: the tested items of the tested samples meet the requirements of FFP2 in NF EN 149+A1:2009-09				

-see next page-



Test Report

No. XKS2020R03020207E

page 4 of 7

3. Test method

3.1 Visual inspection:

The visual inspection shall also include the marking and the information supplied by the manufacturer.

3.2 Material:

1) The conditioning shall be carried out in a manner which ensures that no thermal shock occurs.

A breathing machine is adjusted to 25 cycles/min and 2.0 l/stroke. The particle filtering half mask is mounted on a Sheffield dummy head. For testing, a saturator is incorporated in the exhalation line between the breathing machine and the dummy head, the saturator being set at a temperature in excess of 37°C to allow for the cooling of the air before it reaches the mouth of the dummy head. Their shall be saturated at $(37 \pm 2)^\circ\text{C}$ at the mouth of the dummy head. In order to prevent excess water spilling out of the dummy's mouth and contaminating the particle filtering half mask the head shall be inclined so that the water runs away from the mouth and is collected in a trap.

The breathing machine is brought into operation, the saturator switched on and the apparatus allowed to stabilize. The particle filtering half mask under test shall then be mounted on the dummy head. During the test time at approximately 20 min intervals the particle filtering half mask shall be completely removed from the dummy head and refitted such that during the test period it is fitted ten times to the dummy head.

2) Expose the particle filtering half masks to the following thermal cycle:

a) for 24 h to a dry atmosphere of $(70 \pm 3)^\circ\text{C}$;

b) for 24 h to a temperature of $(-30 \pm 3)^\circ\text{C}$; and allow to return to room temperature for at least 4 h between exposures and prior to subsequent testing.

3.3 Mechanical strength

3.3 Cleaning and disinfection:

Testing shall be done in accordance with 8.4 and 8.5.

With reference to 7.9.2, after clearing and disinfecting the re-usable particle filtering half mask shall satisfy the penetration requirement of the relevant class.

Testing shall be done in accordance with 8.11.1

3.4 Total inward leakage test:

1) The total inward leakage shall be tested using sodium chloride aerosol.

2) A panel of ten clean-shaven persons (without beards or sideburns) shall be selected covering the spectrum of facial characteristics of typical users (excluding significant abnormalities).

3) Test equipment The test atmosphere shall preferably enter the top of the enclosure through a flow distributor, and be directed downwards over the head of the test subject at a minimum flow rate of 0.12 m/s. The concentration of the test agent inside the effective working volume shall be checked to be homogeneous.

The test sequence shall be as follows:

a) Ensure the test atmosphere is OFF.

b) Place the test subject in the enclosure. Connect up the facepiece sampling probe. Have the test subject walk at 6 km/h for 2 min. Measure the test agent concentration inside the particle filtering half mask to establish the background level.

c) Obtain a stable reading.

d) Turn the test atmosphere ON.

e) The subject shall continue to walk for a further 2 min or until the test atmosphere has stabilized.

f) Whilst still walking the subject shall perform the following exercises:

1) walking for 2 min without head movement or talking;

2) turning head from side to side (approx. 15 times), as if inspecting the walls of a tunnel for 2 min;

3) moving the head up and down (approx. 15 times), as if inspecting the roof and floor for 2 min;

4) reciting the alphabet or an agreed text out loud as if communicating with a colleague for 2 min;

5) walking for 2 min without head movement or talking.

g) Record

1) enclosure concentration;

2) the leakage over each exercise period.

h) Turn off the test atmosphere and when the test agent has cleared from the enclosure remove the subject.

After each test, replace the particle filtering half mask by a new sample.

-next page-



Test Report

No. XKS2020R03020207E

page 5 of 7

3. Test method

3.4 Flammability test

The material used shall not present a danger for the wearer and shall not be of highly flammable nature.

When tested, the particle filtering half mask shall not burn or not to continue to burn for more than 5s after removal from the flame.

The particle filtering half mask does not have to be usable after the test.

3.5 Compatibility with skin:

Materials that may come into contact with the wearer's skin shall not be known to be likely to cause irritation or any other adverse effect to health.

Testing shall be done in accordance with 8.4 and 8.5.

3.6 Carbon dioxide content test:

at 95 l/min continuous flow; The exhalation resistance shall not exceed 3 mbar at 160 l/min continuous flow.

Testing shall be done in accordance with 8.9.

3.7 Head harness test:

The head harness shall be designed so that the particle filtering half mask can be donned and removed easily.

The head harness shall be adjustable or self-adjusting and shall be sufficiently robust to hold the particle filtering half mask firmly in position and be capable of maintaining total inward leakage requirements for the device.

Testing shall be done in accordance with 8.4 and 8.5.

3.8 Field of vision test:

The field of vision is acceptable if determined so in practical performance tests.

Testing shall be done in accordance with 8.4.

3.9 Exhalation valve(s):

A particle filtering half mask may have one or more exhalation valve(s), which shall function correctly in all orientations.

Testing shall be done in accordance with 8.2 and 8.9.1.

If an exhalation valve is provided it shall be protected against or be resistant to dirt and mechanical damage and may be shrouded or may include any other device that may be necessary for the particle filtering half mask to comply with 7.9.

Testing shall be done in accordance with 8.2.

Exhalation valve(s), if fitted, shall continue to operate correctly after a continuous exhalation flow of 300 l/min over a period of 30 s.

Testing shall be done in accordance with 8.3.4.

When the exhalation valve housing is attached to the faceblank, it shall withstand axially a tensile force of 10N applied for 10s.

Testing shall be done in accordance with 8.8.

3.10 Carbon dioxide content:

Carbon dioxide content of the inhalation air The carbon dioxide content of the inhalation air (dead space) shall not exceed an average of 1.0% (by volume).

Testing shall be done in accordance with 8.7.

3.11 Clogging test:

For single shift use devices, the clogging test is an optional test. For re-usable devices the test is mandatory.1

Devices designed to be resistant to clogging, shown by a slow increase of breathing resistance when loaded with dust, shall be subjected to the treatment described in 8.10.

The specified breathing resistances shall not be exceeded before the required dust load of 833 mg-h/m³ is reached.

3.12 Demountable parts:

Demountable parts All demountable parts (if fitted) shall be readily connected and secured, where possible by hand.

Testing shall be done in accordance with 8.2.

Test Report

No. XKS2020R03020207E

page 6 of 7

4.Sample photos



Test Description

No. XKS2020R03020207E

page 7 of 7

1. 对本报告有异议, 请在收到报告十五日之内书面提出。

There is any discrepancy in this report, please after receipt of the report made in writing within 15 days.

2. 本报告无讯科标准报告章及签名无效。任何时候, 未经讯科标准书面批准, 不得部分复制检测报告。

This report is considered invalidated without the Special Seal for Inspection of the XKS. At any time, without the written approval of XKS report shall not be part of the copy detection.

3. 委托单位对样品的代表性和资料的真实性负责, 否则本单位不承担任何相关责任。除非本公司进行抽样, 并已在报告中说明, 否则报告中适用于送测的样品(样品信息为客户提供), 不适用于批量。

The authorized agencies responsible for the authenticity of the representative of the sample and the information, otherwise, the unit does not undertake any responsibility. The Report refers only to the tested sample (Sample information is provided by customer) and does not apply to the bulk, unless the sampling has been carried out by the Company and is stated as such in the Report.

4. 本报告仅对所测样品负责, 不做为社会公正数据使用, 也不得用于广告或授权的其他用途。本报告仅作为客户委托、科研、教学或内部质量控制等目的使用。对于测试数据的使用及使用所产生的直接或间接损失及一切法律后果, 本单位不承担任何经济和法律责任。

This report is only responsible for the test sample, not as a social justice data usage. Only for the purpose of customer entrustment, scientific research, teaching or internal quality control. For the use of test data and the use of direct or indirect losses and legal consequences, My company does not undertake any economic and legal responsibility.

5. 不可重复性或不可复测的样品, 委托单位放弃复测的权利。除非本公司进行抽样, 并已在报告中说明, 否则报告中适用于送测的样品(样品信息为客户提供), 不适用于批量。

Do not repetitive or retest samples, entrust unit giving up of retest. The Report refers only to the tested sample (Sample information is provided by customer) and does not apply to the bulk, unless the sampling has been carried out by the Company and is stated as such in the Report.

6. 除非相关政府部门、法律或法院要求, 否则未经公司预先书面同意, 本公司毋需, 也并无义务向法院对有关报告作证。

The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.

7. 如果本公司确定报告被不当地使用, 本公司保留撤回报告的权利, 并有权要求其它适当的额外赔偿。本公司接受样品进行测试的前提是, 该测试报告不能作为针对本公司法律行动的依据。

In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.

8. 若需要在法院审理程序或者仲裁过程中使用测试报告, 客户必须在提交测试样品前将该意图告知本公司。

Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.

9. 若委托方指令本公司对样品进行留样, 所有的样品保留期最长为 15 个工作日或样品性质允许的最短期限, 到期后本公司终止对该样品的任何责任, 并将依照内部管理指令对样品进行处置。若委托方未书面提出本公司对样品进行留样, 本公司将依照内部管理指令进行处置样品。

Fifteen working days later, my company has the right to the complete test after processing the measured samples.

10. 本单位保证测试的客观公正性, 对委托单位的商业信息, 技术文件等商业秘密履行保密义务。任何情况下, 本公司不必提供任何被处理的过期数据或信息。即使本公司事先被告知可能会发生相关的损害, 本公司在任何情况下也不必承担任何损害, 包括(但不限于)补偿性赔偿、利润损失、数据遗失、或任何形式的特殊损害、附带损害、间接损害、从属损害或任何违反约定、违反承诺、侵权(包括疏忽)、产品责任或其他原因的惩罚性损害。

My company to ensure that the test objective, impartial to entrust units of the commercial information, technical documents such as commercial secrets confidential obligations. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

-报告结束-